

## MATERIAL DATASHEET

# ALLOY 001



Designation		Composition (mass as %, reference values)	
Diehl Brass Solutions	001	Cu	58.0
DIN EN symbol	CuZn41Mg	Mg	0.4
DIN EN	CW732R(-DW)	Zn	remainder
UNS	C49400	Pb	≤ 0,10

### Application

- Lead-free standard material for automated machining. Suitable for all types of turned parts.
- The alloy has good hot forming properties.

Products and relevant standards		Physical properties		
Rods (free machining purposes)	EN 12164	Density	g/cm <sup>3</sup>	8.2
Rods (forging stock)	EN 12165	Coefficient of linear thermal expansion: 20 – 200 °C		
Hollow rods (free machining purposes)	EN 12168			
Profiles (general purposes)	EN 12167	• 10 <sup>-6</sup> /K		
		20.34		

Processing properties		Mechanical properties and hardness	
Machinability (CuZn39Pb3 = 100%)	very good	<ul style="list-style-type: none"> <li>• Strength properties and hardness values depend on product, condition and dimension.</li> </ul>	
Hot formability	very good (680 – 740 °C)		
Cold formability	less suitable		

Heat treatment		Corrosion resistance	
Soft annealing	450 – 550 °C	Generally good resistance to neutral, alkaline and organic aqueous solutions.	
Stress relief annealing	250 – 330 °C		

### Diehl Brass Solutions Stiftung & Co. KG

Heinrich-Diehl-Str. 9 | D-90552 Röthenbach a. d. Pegnitz | Phone +49 911 5704-0 | Email: dbs-sales@diehl.com  
[www.diehl.com/metall](http://www.diehl.com/metall)

This material datasheet is for general information purposes only and is not subject to any revision service. Claims may not be derived from it unless there is evidence of intent or gross negligence. The data presented does not provide a warranty that the product is of a specific quality and does not replace any expert advice or customer trials.

#### Risk Disclosure

The tests took place under the test conditions mentioned here. In these tests, selected properties of the alloy can be investigated. The test results are based on the test setup shown, which has specific laboratory conditions. Deviating conditions in the field may have significant effects. Aspects which play a decisive role include, in particular, but not exhaustively, the design of the components, the further processing of the alloy, the processing of the finished parts made with the alloy, transport and storage, the manner and location of use, the installation and the installation situation.

When it comes to properties, the corrosion resistance of the material is a key factor. The DIN standard DIN EN ISO 8044 (formerly DIN 50900) defines corrosion as a reaction of a metallic material with its environment that causes a measurable change in the material and can impair the function of a metal component or an entire system. From a technical point of view, corrosion is a reaction of a material with its environment that causes a measurable change in the material. Corrosion can impair the function of a component or system. Corrosion, as a complex system of interactions, depends on a large number of factors which, in their multifariousness, cannot be fully reproduced under test conditions. The type of corrosion known as dezincification, which occurs with zinc-containing copper alloys that are in contact with drinking water, is familiar to the broad expert public. The purchaser of the alloy is responsible for determining and testing the design, further processing, application areas of products made from the alloy, and any other relevant factors. This is also applicable when determining the dezincification depth that is considered reasonable for the selected area of application. Diehl cannot accept any liability for this, but solely for the information contained in the enclosed product data sheet.