

### MATERIAL DATASHEET

## **ALLOY 458**

Designation	
Diehl Brass Solutions	458
DIN EN symbol	CuZn37Mn3Al2PbSi
DIN EN	CW713R
UNS	-

Compos (mass as %	<b>sition</b> %, reference	values)	
Cu	57.9	Mn	2.0
Pb	0.6	Al	1.7
Fe	0.4	Si	0.6
Ni	≤ 0.5	Zn	remainder



### **Application**

- Engineering material of high strength. For meeting stringent sliding stress requirements.
- Suitable for synchronizer rings, shift forks and valve guides.

Products and relevant s	tandards
Rods (free machining purposes)	EN 12164
Rods (forging stock)	EN 12165
Hollow rods (free machining purposes)	EN 12168
Profiles (general purposes	EN 12167
Seamless, round tubes (general purposes)	EN 12449

Physical properties		
Density	g/cm³	8.12
Coefficient of linear thermal expansion: 20 – 200 °C	• 10 <sup>-6</sup> /K	20.17

Processing properties	
Machinability (CuZn39Pb3 = 100%)	moderate
Hot formability	very good (600 – 700 °C)
Cold formability	limited

r rocessing properties	
Machinability (CuZn39Pb3 = 100%)	moderate
Hot formability	very good (600 – 700 °C)
Cold formability	limited

Mechanical properties and hardness
The strength properties and hardness values are specified in the
relevant product standards.

dimensions.

Corrosion resistance
Generally good resistance to neutral, alkaline and organic aqueous solutions.
Solutions.

The properties depend on the product, the condition and the

# Diehl Brass Solutions Stiftung & Co. KG

Heinrich-Diehl-Str. 9 | D-90552 Röthenbach a. d. Pegnitz | Phone +49 911 5704-0 | Email: dbs-sales@diehl.com

500 − 650 °C 1 − 3 h

350 – 450 °C 1 – 3 h

#### www.diehl.com/metall

Soft annealing

Stress relief annealing

This material datasheet is for general information purposes only and is not subject to any revision service. Claims may not be derived from it unless there is evidence of intent or gross negligence. The data presented does not provide a warranty that the product is of a specific quality and does not replace any expert advice or customer trials.

Version: June 2021