


Brass (Copper-Zinc) MB15



Material Designation	
DIN-EN Symbol	CuZn15
DIN-EN	CW502L
UNS	C23000
JIS	C2300
The Miller Company	C230

Nominal Composition (mass content in %)	
Cu	Balance
Sn	< 0.05
Zn	15
Ni	< 0.2
Fe	< 0.05
Al	< 0.02
Pb	< 0.005
Other	< 0.1

About The Alloy

MB15 is a red brass having fine gloss, good workability, drawability and corrosion resistance.

Among the Copper Zinc Alloys MB15 exhibits a very high electrical and thermal conductivity as well a high modulus of elasticity. The colour of MB15 is due to the increased Zn content already slightly yellow. Applications are found in buildings, personal accessories, cosmetic cases and in the jewellery industry.

MB15 is a single phase Copper alloy and available in a temper condition which allows extraordinary good cold forming and deep drawing with almost no earring.

The alloy is registered with the U.S. EPA as Antimicrobial and with respect to Pb and Cd meets the OEKO-TEX Standard 100.

Physical Properties		
Electrical conductivity soft	19.7	MS/m
Thermal conductivity	159	W/(m·K)
Thermal expansion coefficient **	18.5	10 ⁻⁶ /K
Density	8.8	g/cm ³
Modulus of elasticity	122	GPa = kN/mm ²

Typical Applications

- Jewellery
- Metal ware
- Transistor carriers
- Deep drawing parts
- Stamped-bent parts
- Connectors

* Reference values at room temperature
** Between 20 and 300 °C

Mechanical Properties *)


Temper condition	O30 R 250 H 55	H01 R 300 H 85	H02 R 350 H 105	H03 R 400 H 120	H04 R 440 H 140	H06 R 495 H 160
Tensile strength in N/mm ²	250 - 300	300 - 370	350 - 420	400 - 460	440 - 500	> 495
0.2 % yield Strength in N/mm ²	< 150	> 200	> 270	> 350	> 390	> 450
Elongation A _{L50} %	> 40	> 25	> 15	> 9	> 6	> 3
Vickers hardness HV	55 - 85	85 - 115	105 - 130	120 - 150	140 - 170	> 160
Electrical conductivity in % IACS	34	34	33	33	32	32

Minimum radius of the bending mandrel for 90° bend and strip thickness s

Strip thickness s	Orientation	O30	H01	H02	H03	H04	H06
0.10 ≤ s ≤ 0.25 mm	transverse	0 x s	0 x s	0 x s	0 x s	0 x s	-
	parallel	0 x s	0 x s	0 x s	0 x s	0.5 x s	-
0.25 < s ≤ 0.50 mm	transverse	0 x s	0 x s	0 x s	0 x s	0 x s	-
	parallel	0 x s	0 x s	0 x s	0.5 x s	2 x s	-

*) Reference values

Brass (Copper-Zinc) MB15



Processing Instructions	
Cold forming properties	good
Machinability	sufficient
Electroplating properties	very good
Hot-dip tinning properties	very good
Soldering	very good
Resistance welding	good
Gas shielded arc welding	satisfactory
Laser welding	sufficient

Available Dimensions	
Bright pre-rolled strips 1 to 2.5 mm	
Precision strip thickness from 0.05 to 1.2 mm	
Strip width from 3.0 to 600 mm, but at least 10 times of the strip thickness	
Other widths available on request.	

Available Versions	
Coils with standard outer diameters of 1200 mm	
Strips in reel form with coil weight of up to 1500 kg	
Multipancake up to 2.5 t	
Hot-dip tinned strips	
Profiled strips	
Electroplated strips (tin, nickel)	

Your Local Contact Person		
Europe	USA	Asia

DIEHL
Metal Applications



DIEHL
Metal Applications

<p>Sundwiger Messingwerk GmbH & Co. KG</p> <p>Hönnetalstraße 110 58675 Hemer Germany Phone +49 2372 661-100 Fax +49 2372 661-260 E-Mail: michael.koehler@diehl.com</p> <p>www.diehl.com/metall</p>	<p>The Miller Company</p> <p>275 Pratt Street CT 06450 Meriden USA Phone +1 203 63969-02 Fax +1 203 63969-24 E-Mail: sales@themillerco.com</p> <p>www.diehl.com/metall</p>	<p>Diehl Metall (Shenzhen) Co. Ltd.</p> <p>Block 25 Shatoujiao Free Trade Zone 518081 Shenzhen - P.R. China Phone +86 755 25261454-0 Fax +86 755 25260974 E-Mail: info@diehlmetall.com.cn</p> <p>www.diehl.com/metall</p>
----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------	------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------	-----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------

The information given in this material data sheet, which in any case provides no guarantee of particular characteristics, has been compiled to the best of our knowledge but is given without any obligation on our part. Our liability is determined solely by the individual contract terms, in particular by our general conditions of sale.

We reserve the right to make alterations especially where necessitated by technical developments or changes in availability. Please ask for the latest edition of this material data sheet.